Polymer Works, Hope Street
Dudley, West Midlands DY2 8RS

t: 01384 252555
f: 01384 252373
e: technical@advancedseals.co.uk

http://www.advancedseals.co.uk

Specification Sheet / 01
A350 (C) GREY polyether polyurethane foam

8320
Certificate No. 11738-EMS-001
ISO 9001:2015 ISO 14001:2015

Description

Typical physical properties	
Physical properties are measured using test methods described in the BS4443 series and BS EN ISO 845:1995.	
Nominal piece density range	23.8 – 26.3 kg/m3
Nominal hardness range	120-160 N
Nominal tensile strength	50 kPa min.
Nominal elongation at break	90% min.
UV Stability	Poor

Foam Classification (BS3379)	
Nominal Classification	A

Flammability characterisitics	
Complies with the requirements of Schedule 1, Part 1, The Furniture and Furnishings (Fire) (Safety) Amended Regulations 1989.	
Under Writers Laboratories - UL94 HF1 Classification	

Change Control Date	***Change***
11/09/14	Created

The above figures are average values.
We recommend that you examine any material you select to ensure its suitability for your application.
Tolerance(s) applied in accordance with ASG specification No WI007 (https://bit.ly/3nKm6Hj) unless otherwise stated.
Our standard terms and conditions of trading (https://bit.ly/3b3mThw) apply at all times.