

Specification Sheet (Superceded) / 01 A335 General Purpose Silicone Rubber Sheet



Certificate No. 11738-EMS-001
ISO 9001:2015 ISO 14001:2015

Property	Average Value(s)
Temperature Range	-60 °C - +230 °C
Product Form	Continuous solid sheeting
Applications	The general purpose range was sepcifically designed as a calandared grade for producing continuous solid sheeting. This is primarily used for belting and sheeting
Flammability characteristics	The products have a Llimited Oxygen Index (LOI) of 24% (BS 2872 part i) and comply with the following flammability specification: FAR 25.853 (a)(1)(iv) and (a)(1)(v) horizontal flame tests CAA specifications 8 issue 2 (2.2)(c) and (d) horizontal flammability tests

Thermal Properties

Property	Typical Values	Test Method
Thermal Conductivity	0.86 Kjm ⁻¹ hr ⁻¹ K ⁻¹ (0.24 Wm ⁻¹ K)	VDE 0304
Brittle Point	-80	ASTM D 746

Property	Average Value(s)
Environmental Resistance	the products have excellent resistance to ozone, oxidation, ultraviolet light, corona discharge, cosmetic radiation, raidation and weathering in general. Typical radiation resistance is greater than 10 ⁵ grays (greater than 10 ⁷ rads).
Pigmentability	The products are available in a full range of standard colours, including translucent, and can be colour matched to customer requirements.

Electrical Properties

Property	Typical Figures	Test Method
Dialectric strength (KV/mm)	23	VDE0303
Dialectric constant	2.9	VDE0303
Dissipation factor @ 50 liz (tan delta)	3 x 10E-4	VDE0303
Volume resistance (Ohm.cm)	3 x 10E15	VDE0303
Power factor	1.8 x 10E ⁻³	ASTM D 150

Property	Average Value(s)
Chemical Composition	This range of polydimothylsiloxane have been cross-linked with an organic peroxide. They contain a high performace heat stability additive, small quantities of ground quartz filler and a pigment, if required. These products can all be processed to remove

Property	GP40° Specification Limits	GP40° Typical value	Test Method
Shore A	40° ± 5°	42	BS 906 Part A26
Tensile Strength (MPa)	4.0 min	6.5	BS 903 Part A2
Tear Strength (N/mm)	8 min	15	BS 903 Part A3 Cutter type C

Specification Sheet (Superceded) / 02 A335 General Purpose Silicone Rubber Sheet



Certificate No. 11738-EMS-001
ISO 9001:2015 ISO 14001:2015

Elongation at break	300% min	440%	BS 903 Part 2
Compression Set	35% Max	30%	BS 903 Part A6

Property	GP50° Specification Limits	GP50° Typical value	Test Method
Shore A	50° ± 5°	50	BS 906 Part A26
Tensile Strength (MPa)	5.5 min	8	BS 903 Part A2
Tear Strength (N/mm)	10 min	11.5	BS 903 Part A3 Cutter type C
Elongation at break	250% min	380%	BS 903 Part 2
Compression Set	30% Max	28%	BS 903 Part A6

Property	GP60° Specification Limits	GP60° Typical value	Test Method
Shore A	60° ± 5°	60	BS 906 Part A26
Tensile Strength (MPa)	5.5 min	9	BS 903 Part A2
Tear Strength (N/mm)	12.5 min	13	BS 903 Part A3 Cutter type C
Elongation at break	250% min	320%	BS 903 Part 2
Compression Set	30% Max	26%	BS 903 Part A6

Property	GP70° Specification Limits	GP70° Typical value	Test Method
Shore A	70° ± 5°	70	BS 906 Part A26
Tensile Strength (MPa)	12.5 min	12	BS 903 Part A2
Tear Strength (N/mm)	8 min	15	BS 903 Part A3 Cutter type C
Elongation at break	200% min	305%	BS 903 Part 2
Compression Set	30% Max	20%	BS 903 Part A6

Change Control Date	Change
26/07/2013	Created



The above figures are average values.
We recommend that you examine any material you select to ensure its suitability for your application.
Tolerance(s) applied in accordance with ASG specification No WI007 (<https://bit.ly/3nKm6Hj>) unless otherwise stated.
Our standard terms and conditions of trading (<https://bit.ly/3b3mThw>) apply at all times.

