

Polymer Works, Hope Street
Dudley, West Midlands DY2 8RS

t: 01384 252555
f: 01384 252373
e: technical@advancedseals.co.uk



Specification Sheet / OI A305 Fine Ribbed Matting



Properties	Units	Standards	Values
Colour		Black	
Elongation at Break	%	ASTM D412	250
Working Temperature	°C		-20 / 70 (90 Intermittent)
Tensile Strength	mpa	ASTM D412	2.8
Specific Gravity	g/cm3	ASTM D2240	1.5

Compression Set	Cond. Temp.	Unit	Values
Standard ASTM D395 Method B	70°C 22h	% Max	30

Change Control Date	Change
08/12/2016	Created



The above figures are average values.
We recommend that you examine any material you select to ensure its suitability for your application.
Tolerance(s) applied in accordance with ASG specification No WI007 (<http://goo.gl/mc0862>) unless otherwise stated.
Our standard terms and conditions of trading (<http://goo.gl/zjcfRi>) apply at all times.

