Polymer Works, Hope Street Dudley, West Midlands DY2 8RS

t: 01384 252555 f: 01384 252373 e: technical@advancedseals.co.uk

Specification Sheet / 01 A347 Soft Grade Expanded PVC

Property	Result
Roll Length	From 25 m to 100 m according to the thickness
Thickness (mm)	2, 3, 4, 5, 6, 8, 10, 12, 15, 18, 20
Width	1000 mm - 1400 mm
Density	120 kg/m ³
Colour	White / Grey / Brown / Black

Test	Description	Result
Resistance to deformation under Compression (DIN 53576/B)	Crushing on initial thickness of 25%	69.7
Resistance to deformation under Compression (DIN 53576/B)	Crushing on initial thickness of 40%	109.7
Resistance to deformation under Compression (DIN 53576/B)	Crushing on initial thickness of 65%	301.0
Residual deformation after Compression (DIN 53572) - Room temperature, crushing 50%, 72 hours	Residual deformation after 30 hours	7.9
Residual deformation after Compression (DIN 53572) - Room temperature, crushing 50%, 72 hours	Residual deformation after 4 hours	3.1
Residual deformation after Compression (DIN 53572) - Room temperature, crushing 50%, 72 hours	Residual deformation after 24 hours	1.1
Dimensional stability after heat treatment	4h at 60 °C	1.0
Dimensional stability after heat treatment	4h at 60 °C (Transver.dir)	0.1
Dimensional stability after heat treatment	4h at -30 °C (Longitu.dir)	0.6
Dimensional stability after heat treatment	4h at -30° C (Transver.dir)	0.6

Resistance to tensile strength / maximum extension (DIN 53571) And change in terms of dimensions of original sample and after different treatments / ageing.		
Description		
Original Sample		
Warm (60°C)		
Cold (-30°C)		
Ageing 24h in steam (hidrolysis 100°C DIN 53578)		
In mineral oil DIN 53428		
In alcohol DIN 53428		
In alkaline solution (NaC1 25%) DIN 53428		
In water DIN 53428		
In petrol (iso-octane) DIN 53428		
In concentrated acid solution (H2 SO4 40%) DIN 53428		
In concentrated alkaline solution (NaOH 40%) DIN 53428		
Change Control Date	Change	





http://www.advancedseals.co.uk

Polymer Works, Hope Street Dudley, West Midlands DY2 8RS

t: 01384 252555 f: 01384 252373 e: technical@advancedseals.co.uk

Specification Sheet / 02 A347 Soft Grade Expanded PVC

29/07/2013	Created
25/09/2013	Added descriptive properties



The above figures are average values.

We recommend that you examine any material you select to ensure its suitability for your application. Tolerance(s) applied in accordance with ASG specification No WI007 (https://bit.ly/3nKm6Hj) unless otherwise stated. Our standard terms and conditions of trading (https://bit.ly/3b3mThw) apply at all times.



Certificate No. 11738-EMS-001 ISO 9001:2015 ISO 14001:2015



http://www.advancedseals.co.uk