

Specification Sheet / 01 A330 Black Open Cell Sponge



Certificate No. 11738-EMS-001
ISO 9001:2015 ISO 14001:2015

Property	Test Method	Value
Density (Average) (lb./ft3)	ASTM D1056	26
Colour	-	Black
Polymer	-	Natural Rubber
Compression Deflection (psi)	ASTM D1056 at 25% compression	5 - 10
Compression Deflection Change after Oven Aging (%)	ASTM D1056 - 168 hours at 158°F (70°C)	+/- 20
Compression Set (% max.)	ASTM D1056 50% deflection at 158°F (70°C)	15
Finish	Cloth Finish with Chalk Coating	
Temperature Range	-	-20°F to +160°F

Change Control Date	Change
30/07/2013	Created



The above figures are average values.
We recommend that you examine any material you select to ensure its suitability for your application.
Tolerance(s) applied in accordance with ASG specification No W1007 (<https://bit.ly/3nKm6Hj>) unless otherwise stated.
Our standard terms and conditions of trading (<https://bit.ly/3b3mThw>) apply at all times.

